

For more information and technical assistance contact:

Chevron Phillips Chemical Company LP  
P.O. Box 4910  
The Woodlands, TX 77387-4910  
800.231.1212



PREMIUM EXTRUSION AND RIGID PACKAGING RESINS

## Marlex® 9346

HIGH DENSITY POLYETHYLENE

**This high performance, HDPE is tailored for demanding pressure pipe applications that require:**

- Good long-term hoop strength
- Very high melt strength
- Outstanding low-temperature toughness

**This resin meets this specification:**

- ASTM D4976 - PE 235

**Typical applications for 9346 include:**

- Municipal, industrial, and mining pipe
- Oil and gas-gathering pipe

**When blended with an approved black concentrate, this material meets or exceeds:**

- ASTM D3350, class 445474C
- NSF Standards 14 and 61 for potable water
- PPI designation PE 4710

NOMINAL PHYSICAL PROPERTIES <sup>(1)</sup>			
	English	SI	Method
Density	---	0.948 g/cm <sup>3</sup>	ASTM D1505
Flow Rate (HLM1, 190/21.6)	---	9.0 g/10 min	ASTM D1238
Tensile Strength at Yield, 2 in/min, Type IV bar	3,400 psi	23 MPa	ASTM D638
Elongation at Break, 2 in/min, Type IV bar	800%	800%	ASTM D638
Flexural Modulus, 2% Secant - 16:1 span:depth, 0.5 in/min	130,000 psi	900 MPa	ASTM D790
PENT Slow Crack Growth	>500 h	>500 h	ASTM F1473

  

NOMINAL PIPE PROPERTIES <sup>(2)</sup>			
	English	SI	Method
Hydrostatic Design Basis, 73°F (23°C)	1,600 psi	11.0 MPa	ASTM D2837
Hydrostatic Design Basis, 140°F (60°C)	800 psi	5.5 MPa	ASTM D2837

1. The nominal properties reported herein are typical of the product, but do not reflect normal testing variance and therefore should not be used for specification purposes. Values are rounded. The physical properties were determined on compression molded specimens that were prepared in accordance with Procedure C of ASTM D4703, Annex A1 or ASTM F1473.

2. The nominal pipe properties were determined on pipe extruded from a pellet blend of 9346 and an approved black concentrate.

MSDS #240370

Revision Date April, 2007

Another quality product from



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.